

Eastman **OPTIFILM**^{**}

Reduce emulsion wall paint odor

Introduction

Eastman Texanol[™] ester alcohol is an excellent coalescent in emulsion paint applications and imparts desirable properties such as scrub resistance, color development, and package stability in paints. In certain situations, the mild but characteristic odor of Texanol may not be ideal for some applications.

For these applications, the use of Eastman Optifilm[™] enhancer 300 is highly recommended. It imparts similar desirable properties such as good scrub resistance and color development but with very low odor.

This technical tip compares the odor characteristics of three commercial architectural flat emulsion wall paints; one containing no coalescent—one containing Texanol one containing Optifilm 300.

The comparison shows that the paint incorporating Optifilm 300 has a very low odor comparable to paint containing no coalescent and lower than the paint containing Texanol.



Procedure

- 1. A standard flat wall paint was diluted by 20% with deionized water and split into 6 samples.
- 2. Texanol and Optifilm 300 were each added to two samples at 0.5% parts by weight based on the original undiluted weight of paint.
- 3. Two samples were not coalesced and were used as "blanks." After 24 hours, the inside of 5-liter lacquer-lined tins were coated with 5 g of paint using a sponge. A new sponge was used for each application, which prevented cross contamination of the samples.
- 4. The paints were allowed to dry for approximately 1 hour at ambient and then sealed with lids. The tins were stored at 23°C throughout the experiment.
- Twenty-four hours after application, 10 judges, not connected with the coatings laboratory and unfamiliar with the coalescents and their odors, were asked to evaluate the paints' odor, ranking the 6 samples from least odor to most odor. This was repeated after 11 days using 8 of the original 10 judges.
- 6. A statistical analysis called a Friedman's test was carried out. This test calculates a Chi-square statistic based on the rankings by each judge. A low p value indicates the Chi-square value is statistically significant.

Judges odor ratings and statistical analysis

Figure 2. Graphical comparison of judges' odor rating @ 24 hours and @ 11 days



6 5 4 > 3 2 1 А В С D Е F G Н Judge



Statistical analysis*

- Each data point is the average (mean) of the odor rating each judge gave two tins of each paint.
- The graphs show the judges have rated the tins consistently, within themselves, on each occasion.
- The difference between the odor rating at 24 hours and at 11 days was calculated for each judge, and each paint; i.e., the difference between each pair of points on the graphs. The average (mean) of these differences was 0.01042. A Students T-Test was carried out which concluded this mean difference was not statistically significantly different from 0 (Prob> [t] = 0.9163).
- * There is acceptable agreement between the odor rating given by each judge, to each paint, after 24 hours and after 11 days. The data is therefore valid for further statistical analysis.

Plot for paint with Eastman Optifilm[™] enhancer 300













Statistical analysis

- Figures 3 and 4 are "box and whisker" plots. The central line of each box denotes the median odor rating for each paint. The "box" contains 50% of the data. The "whiskers" denote the spread of the data, and single points indicate possible outliers (relative to that paint only).
- These plots show at both 24 hours and at 11 days that Eastman Texanol[™] ester alcohol measures higher in odor than Eastman Optifilm[™] enhancer 300 and the blank sample with no coalescent added.
- The overlap between the boxes for the Optifilm 300 and the blank sample indicates they are not significantly different from each other.
- Further statistical analysis was performed via Friedman's test. This test models the ratings of *n* judges on *k* treatment: (paints). The test parameter calculated was statistically significant, indicating the paints are different and the judges' odor ratings are correlated.

Conclusion

These statistical analyses confirm the paint incorporating Optifilm 300 has an odor comparable with the "blank" sample containing no coalescent and lower than the paint containing Texanol.



Eastman Chemical Company

Corporate Headquarters P.O. Box 431 Kingsport, TN 37662-5280 U.S.A.

Telephone: U.S.A. and Canada, 800-EASTMAN (800-327-8626) Other Locations, (1) 423-229-2000 Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd. Suite 1116 Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800 Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614 2909 VA Capelle aan den IJssel The Netherlands

Telephone: (31) 10 2402 111 Fax: (31) 10 2402 100

Eastman (Shanghai) Chemical

Commercial Company Ltd. Building 3, Yaxin Science & Technology Park Lane 399 Shengxia Road, Pudong New District 201210, Shanghai, P.R. China

Telephone: (86) 21 6120-8700 Fax: (86) 21 5027-9229

Eastman Chemical Japan Ltd.

Anzen Building 16F 1-6-6 Moto Akasaka Minato-ku, Tokyo 107-0051 Japan

Telephone: (81) 3-3475-9510 Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

9 North Buona Vista Drive #05-01 The Metropolis Tower 1 Singapore 138588

Telephone: (65) 6831-3100 Fax: (65) 6732-4930

www.eastman.com

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company makes no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of their suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2015 Eastman Chemical Company. Eastman, Optifilm, Texanol, and The results of insight are trademarks of Eastman Chemical Company.